



Developed by  CARBON PRODUCTS

Technical Data Sheet TDS

Product Specification

<i>Physical Properties</i>	<i>Test Method</i>	<i>Values</i>
Specific gravity:	ASTM D1817	1.86 typical
Carbon, C:	-----	84.00% typical
Volatiles:	ASTM D4527	3.00% typical
Moistures (Heat Loss):	ASTM D1509	0.50% typical
Ash:	ASTM D1506	16.00% typical
pH:	ASTM D1512	8.8 typical
Screen Analysis:	CFI Test Procedure	Maximum 1.0%retained on 325 mesh
Pour Density:	ASTM D1513	170 kg/m3 typical
Bulk Density:	ASTM D4894	250 kg/m3 typical
Bulk Density:	ASTM D4894	250 kg/m3 typical
Tint Strength:	ASTM D3265	48 typical

Issue No: 2

Issue Date: 02/15/18

Revision No. 0

Revision Date: NA



A Finer Choice for Your Formula.

Locations in Bluefield, VA and Tams, WV, USA • 1.276.322.4675 • CFIcarbonproducts.com